

PRODUCT DATA SHEET FOR DWU 2/20
EPS S 040 FACADE

ENERPOR

1. Product description:

EPS S 040 FACADE polystyrene thermal insulation panels are manufactured from expanded polystyrene in accordance with PN-EN 13163+A1:2015-03 "Thermal insulation products for buildings. Factory made expanded polystyrene (EPS) products. Specification." These are rectangular panels with straight or milled edges. Standard panels are produced in the following dimensions: length 1000 mm, width 500 mm, thickness 20 to 300 mm in 10 mm increments.

2. Application:

EPS S 040 FACADE polystyrene panels are intended for thermal insulation in the building industry, mainly for facades,. These products are specifically intended for:

- *thermal insulation of walls with cladding elements and ventilated air gap*
- *thermal insulation of walls in external composite insulating systems*
- *thermal insulation of tie beams as stay-in-place formwork under plaster*
- *thermal insulation of lintels and jambs*
- *thermal insulation in prefabricated external sandwich panels*
- *thermal insulation of the underside of ceilings in external composite insulating systems*
- *thermal insulation and stay-in-place formwork for reinforced concrete ceilings*
- *thermal insulation under load-bearing structures*
- *thermal insulation of walls including BSO, ETICS (light - wet) or (light - dry)*

3. Technical specifications:

Code of designation: EPS-EN 13163-T2-L2-W2-S_b5-P5-BS75-DS(N)2-DS(70,-)2-TR80

Property	Class/level	Tolerance/Requirements
Thickness	T2	± 2 mm
Length	L2	± 2 mm
Width	W2	± 2 mm
Rectangular shape	S _b 5	± 5 mm/m
Flatness	P5	5 mm
Flexural strength	BS75	≥ 75 kPa
Dimensional stability under laboratory conditions	DS(N)2	± 0,2%
Dimensional stability under specified temperature and humidity conditions	DS(70,-)2	± 2%
Tensile strength perpendicular to faces	TR80	≥ 80 kPa
Declared thermal conductivity coefficient W/(m·K)	-	0,040 W/(m·K)
Class of reaction to fire	E	-

**PRODUCT DATA SHEET FOR DWU 2/20
EPS S 040 FACADE**

ENERPOR

Declared thermal resistance R_d [$m_2 \cdot [K/W]$]

d [mm]	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150
R_d	-	0,50	0,75	1,00	1,25	1,50	1,75	2,00	2,25	2,50	2,75	3,00	3,25	3,50	3,75
d [mm]	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
R_d	4,00	4,25	4,50	4,75	5,00	5,25	5,50	5,75	6,00	6,25	6,50	6,75	7,00	7,25	7,50

4. Packaging:

Thickness (mm)		20	30	40	50	60	70	80	90	100	110	120	130	140	150
Quantity (pieces)		30	20	15	12	10	8	7	6	6	5	5	4	4	4
Volume (m ³)		0,3	0,3	0,3	0,3	0,3	0,28	0,28	0,27	0,3	0,28	0,3	0,26	0,28	0,3
Panel surface (m ²)		15	10	7,5	6	5	4	3,5	3	3	2,5	2,5	2	2	2
Thickness (mm)	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
Quantity (pieces)	3	3	3	3	3	2	2	2	2	2	2	2	2	2	2
Volume (m ³)	0,24	0,26	0,27	0,29	0,3	0,21	0,22	0,23	0,24	0,25	0,26	0,27	0,28	0,29	0,3
Panel surface (m ²)	1,5	1,5	1,5	1,5	1,5	1	1	1	1	1	1	1	1	1	1

5. Use/Storage/Transport:

It is recommended that the product does not come into contact with any materials in the building that react with EPS causing them to dissolve or swell (with adhesives containing solvents, wood protection agents).

The panels should be transported and stored in a way that protects them from damage and weather conditions such as UV radiation, strong sunlight and rainfall (required drying of the panels before installation).

The product does not contain hazardous substances as defined in the REACH Regulation. No hazards when using the product correctly and following health and safety rules.

Trade Office:
„ENERPOR” Sp z o.o. 25-620 Kielce ul. Kolberga 11
e-mail: bok@enerpor.pl