

PRODUCT DATA SHEET FOR DOP 14/21
EPS 200 035 PARKING

ENERPOR

1. Product description:

EPS 200 035 PARKING polystyrene thermal insulation panels are manufactured from expanded polystyrene in accordance with EN 13163:2012+A1:2015 "Thermal insulation products for buildings. Factory made expanded polystyrene (EPS) products. Specification." These are rectangular panels with straight or milled edges. Standard panels are produced in the following dimensions: length 1000 mm, width 500 mm, thickness 10 to 300 mm in 10 mm increments.

2. Application:

EPS 200 035 PARKING polystyrene panels are intended for thermal insulation in the building industry, with main purpose of insulation at car parks. These products are specifically intended for:

- *thermal insulation of plinths in external composite insulating systems*
- *thermal insulation of walls below ground level with heavily loaded waterproofing*
- *heavily loaded thermal insulation of floors under a subfloor*
- *heavily loaded thermal insulation of floors on a ground with subfloor*
- *thermal insulation of load-bearing structures under tile roofing*
- *thermal insulation of flat roofs*
- *structural filling of road embankments, railway abutments, bridges and other engineering structures*
- *warstwa izolująca przed przemarzaniem w konstrukcjach drogowych*
- *thermal insulation of floors in industrial buildings with a service load of up to 6 tonnes/m²*

3. Technical specifications:

Code of designation: EPS-EN 13163-T2-L3-W3-S_b5-P10-BS250-CS(10)200-DS(N)5-DS(70,-)2-DLT(1)5

Property	Class/level	Tolerance/Requirements
Thickness	T2	± 2 mm
Length	L3	± 0,6 % or ± 3 mm
Width	W3	± 0,6 % or ± 3 mm
Rectangular shape	S _b 5	± 5 mm
Flatness	P10	10 mm
Flexural strength	BS 250	≥ 250 kPa
Compressive stress at 10 % deformation	CS(10)200	≥ 200 kPa
Dimensional stability under laboratory conditions	DS(N)5	± 0,5%
Dimensional stability under specified temperature and humidity conditions	DS(70,-)2	± 2%
Deformation under specific compressive load and temperature conditions	DLT(1)5	≤ 5%
Declared thermal conductivity coefficient W/(m·K)	-	0,035W/(m·K)
Class of reaction to fire	E	-

**PRODUCT DATA SHEET FOR DOP 14/21
EPS 200 035 PARKING**

ENERPOR

Declared thermal resistance $R_d [m_2 \cdot [K/W]$

d [mm]	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150
R_d	0,25	0,55	0,85	1,10	1,40	1,70	2,00	2,25	2,55	2,85	3,10	3,40	3,70	4,00	4,25
d [mm]	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
R_d	4,55	4,85	5,10	5,40	5,70	6,00	6,25	6,55	6,85	7,10	7,40	7,70	8,00	8,25	8,50

4. Packaging:

Thickness (mm)		20	30	40	50	60	70	80	90	100	110	120	130	140	150
Quantity (pieces)		30	20	15	12	10	8	7	6	6	5	5	4	4	4
Volume (m ³)		0,3	0,3	0,3	0,3	0,3	0,28	0,28	0,27	0,3	0,28	0,3	0,26	0,28	0,3
Panel surface (m ²)		15	10	7,5	6	5	4	3,5	3	3	2,5	2,5	2	2	2
Thickness (mm)	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
Quantity (pieces)	3	3	3	3	3	2	2	2	2	2	2	2	2	2	2
Volume (m ³)	0,24	0,26	0,27	0,29	0,3	0,21	0,22	0,23	0,24	0,25	0,26	0,27	0,28	0,29	0,3
Panel surface (m ²)	1,5	1,5	1,5	1,5	1,5	1	1	1	1	1	1	1	1	1	1

5. Use/Storage/Transport:

It is recommended that the product does not come into contact with any materials in the building that react with EPS causing them to dissolve or swell (with adhesives containing solvents, wood protection agents).

The panels should be transported and stored in a way that protects them from damage and weather conditions such as UV radiation, strong sunlight and rainfall (required drying of the panels before installation).

The product does not contain hazardous substances as defined in the REACH Regulation. No hazards when using the product correctly and following health and safety rules.

Trade Office:
„ENERPOR” Sp z o.o. 25-620 Kielce ul. Kolberga 11
e-mail: bok@enerpor.pl