

**PRODUCT DATA SHEET FOR DOP 5/21**  
**EPS S 033 FACADE**

**ENERPOR**

**1. Product description:**

*EPS S 033 FACADE polystyrene thermal insulation panels are manufactured from expanded polystyrene in accordance with EN 13163:2012+A1:2015 "Thermal insulation products for buildings. Factory made expanded polystyrene (EPS) products. Specification." These are rectangular panels with straight or milled edges. Standard panels are produced in the following dimensions: length 1000 mm, width 500 mm, thickness 20 to 300 mm in 10 mm increments.*

**2. Application:**

*EPS S 033 FACADE polystyrene panels are intended for thermal insulation in the building industry, mainly for facades,. These products are specifically intended for:*

- *thermal insulation of walls with cladding elements and ventilated air gap*
- *thermal insulation of tie beams as stay-in-place formwork under plaster*
- *thermal insulation of lintels and jambs*
- *thermal insulation in prefabricated external sandwich panels*
- *thermal insulation of the underside of ceilings in external composite insulating systems*
- *thermal insulation under load-bearing structures*
- *thermal insulation of walls including BSO, ETICS (light - wet) or (light – dry)*
- *thermal insulation of three-layer walls*
- *thermal insulation of partition walls*
- *thermal insulation of rafter roofs*
- *thermal insulation of floors on joists*
- *thermal insulation of ventilated flat roofs*

**3. Technical specifications:**

*Code of designation: EPS-EN 13163-T2-L2-W2-S<sub>b</sub>5-P5-BS75-DS(N)2-DS(70,-)2-TR80*

Property	Class/level	Tolerance/Requirements
Thickness	<i>T2</i>	$\pm 2 \text{ mm}$
Length	<i>L2</i>	$\pm 2 \text{ mm}$
Width	<i>W2</i>	$\pm 2 \text{ mm}$
Rectangular shape	<i>S<sub>b</sub>5</i>	$\pm 5 \text{ mm/m}$
Flatness	<i>P5</i>	$5 \text{ mm}$
Flexural strength	<i>BS75</i>	$\geq 75 \text{ kPa}$
Dimensional stability under laboratory conditions	<i>DS(N)2</i>	$\pm 0,2\%$
Dimensional stability under specified temperature and humidity conditions	<i>DS(70,-)2</i>	$\pm 2\%$
Tensile strength perpendicular to faces	<i>TR80</i>	$\geq 80 \text{ kPa}$
Declared thermal conductivity coefficient W/(m·K)	-	$0,033 \text{ W/(m·K)}$
Class of reaction to fire	<i>E</i>	-

**PRODUCT DATA SHEET FOR DOP 5/21  
EPS S 033 FACADE**

**ENERPOR**

Declared thermal resistance  $R_D [m_2 \cdot [K/W]$

<b>d [mm]</b>	<b>20</b>	<b>30</b>	<b>40</b>	<b>50</b>	<b>60</b>	<b>70</b>	<b>80</b>	<b>90</b>	<b>100</b>	<b>110</b>	<b>120</b>	<b>130</b>	<b>140</b>	<b>150</b>	
<b>R<sub>D</sub></b>	0,60	0,90	1,20	1,50	1,80	2,10	2,40	2,70	3,00	3,30	3,60	3,90	4,20	4,50	
<b>d [mm]</b>	<b>160</b>	<b>170</b>	<b>180</b>	<b>190</b>	<b>200</b>	<b>210</b>	<b>220</b>	<b>230</b>	<b>240</b>	<b>250</b>	<b>260</b>	<b>270</b>	<b>280</b>	<b>290</b>	<b>300</b>
<b>R<sub>D</sub></b>	4,80	5,15	5,45	5,75	6,05	6,35	6,65	6,95	7,25	7,55	7,85	8,15	8,45	8,75	9,05

**4. Packaging:**

Thickness (mm)	20	30	40	50	60	70	80	90	100	110	120	130	140	150	
Quantity (pieces)	30	20	15	12	10	8	7	6	6	5	5	4	4	4	
Volume (m <sup>3</sup> )	0,3	0,3	0,3	0,3	0,3	0,28	0,28	0,27	0,3	0,28	0,3	0,26	0,28	0,3	
Panel surface (m <sup>2</sup> )	15	10	7,5	6	5	4	3,5	3	3	2,5	2,5	2	2	2	
Thickness (mm)	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
Quantity (pieces)	3	3	3	3	3	2	2	2	2	2	2	2	2	2	2
Volume (m <sup>3</sup> )	0,24	0,26	0,27	0,29	0,3	0,21	0,22	0,23	0,24	0,25	0,26	0,27	0,28	0,29	0,3
Panel surface (m <sup>2</sup> )	1,5	1,5	1,5	1,5	1,5	1	1	1	1	1	1	1	1	1	1

**5. Use/Storage/Transport:**

It is recommended that the product does not come into contact with any materials in the building that react with EPS causing them to dissolve or swell (with adhesives containing solvents, wood protection agents).

The panels should be transported and stored in a way that protects them from damage and weather conditions such as UV radiation, strong sunlight and rainfall (required drying of the panels before installation).

The product does not contain hazardous substances as defined in the REACH Regulation. No hazards when using the product correctly and following health and safety rules.

Trade Office:  
**„ENERPOR” Sp z o.o. 25-620 Kielce ul. Kolberga 11**  
**e-mail: bok@enerpor.pl**