

**PRODUCT DATA SHEET FOR DOP 17/21**  
**EPS 100 36 ROOF/FLOOR**

**ENERPOR**

**1. Product description:**

*EPS 100 036 ROOF/FLOOR polystyrene thermal insulation panels are manufactured from expanded polystyrene in accordance with EN 13163:2012+A1:2015 "Thermal insulation products for buildings. Factory made expanded polystyrene (EPS) products. Specification." These are rectangular panels with straight or milled edges. Standard panels are produced in the following dimensions: length 1000 mm, width 500 mm, thickness 10 to 300 mm in 10 mm increments.*

**2. Application:**

*EPS 100 036 ROOF/FLOOR polystyrene panels are intended for thermal insulation in the building industry, mainly for roofs and floors. These products are specifically intended for:*

- *thermal insulation of plinths in external composite insulating systems*
- *normally loaded thermal insulation of walls below ground level with waterproofing*
- *wall and roof sandwich panels with tar paper and metal cladding*
- *thermal insulation of floors under prefabricated slab subfloors*
- *normally loaded thermal insulation of floors under a subfloor*
- *normally loaded thermal insulation of floors on a ground with subfloor*
- *thermal insulation of flat roofs, without access*
- *thermal insulation of floors in residential buildings with a service load up to 3 tonnes/m<sup>2</sup>*
- *thermal insulation of flat roofs*

**3. Technical specifications:**

*Code of designation: EPS-EN 13163-T2-L3-W3-S<sub>b</sub>5-P10-BS150-CS(10)100-DS(N)5-DS(70,-)2*

Property	Class/level	Tolerance/Requirements
Thickness	T2	± 2 mm
Length	L3	± 0,6 % or ± 3 mm
Width	W3	± 0,6 % or ± 3 mm
Rectangular shape	S <sub>b</sub> 5	± 5 mm
Flatness	P10	10 mm
Flexural strength	BS150	≥ 150 kPa
Compressive stress at 10 % deformation	CS(10)100	≥ 100 kPa
Dimensional stability under laboratory conditions	DS(N)5	± 0,5%
Dimensional stability under specified temperature and humidity conditions	DS(70,-)2	± 2%
Declared thermal conductivity coefficient W/(m·K)	-	0,036 W (m·K)
Class of reaction to fire	E	-

**PRODUCT DATA SHEET FOR DOP 17/21**  
**EPS 100 36 ROOF/FLOOR**

**ENERPOR**

Declared thermal resistance  $R_D [m_2 \cdot [K/W]$

$d$ [mm]	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150
$R_D$	0,25	0,55	0,80	1,10	1,35	1,65	1,90	2,20	2,50	2,75	3,05	3,30	3,60	3,85	4,15
$d$ [mm]	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
$R_D$	4,40	4,70	5,00	5,25	5,55	5,80	6,10	6,35	6,65	6,90	7,20	7,50	7,75	8,05	8,30

**4. Packaging:**

Thickness (mm)		20	30	40	50	60	70	80	90	100	110	120	130	140	150
Quantity (pieces)		30	20	15	12	10	8	7	6	6	5	5	4	4	4
Volume (m <sup>3</sup> )		0,3	0,3	0,3	0,3	0,3	0,28	0,28	0,27	0,3	0,28	0,3	0,26	0,28	0,3
Panel surface (m <sup>2</sup> )		15	10	7,5	6	5	4	3,5	3	3	2,5	2,5	2	2	2
Thickness (mm)	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
Quantity (pieces)	3	3	3	3	3	2	2	2	2	2	2	2	2	2	2
Volume (m <sup>3</sup> )	0,24	0,26	0,27	0,29	0,3	0,21	0,22	0,23	0,24	0,25	0,26	0,27	0,28	0,29	0,3
Panel surface (m <sup>2</sup> )	1,5	1,5	1,5	1,5	1,5	1	1	1	1	1	1	1	1	1	1

**5. Use/Storage/Transport:**

It is recommended that the product does not come into contact with any materials in the building that react with EPS causing them to dissolve or swell (with adhesives containing solvents, wood protection agents).

The panels should be transported and stored in a way that protects them from damage and weather conditions such as UV radiation, strong sunlight and rainfall (required drying of the panels before installation).

The product does not contain hazardous substances as defined in the REACH Regulation. No hazards when using the product correctly and following health and safety rules.

Trade Office:  
**„ENERPOR” Sp z o.o. 25-620 Kielce ul. Kolberga 11**  
**e-mail: bok@enerpor.pl**